


Model Grey

3D Printing Material for Dental and Orthodontic Models



- Material designed for 3D printing of dental and orthodontic models
- Ultra-fast technology
- Flawless surface detail
- Thermoforming release agent
- Ideal for thermoforming aligners
- Powered by KeyPrint®

Property	Procedure	Model
Maximum Tensile Strength	ASTM D638	>50 MPa
Tensile Modulus	ASTM D638	>1700 MPa
Elongation at Break	ASTM D638	5%
Maximum Flexural Strength	ASTM D790	>70 MPa
Flexural Modulus	ASTM D790	>1940 MPa
Viscosity @ 25C (cP)	ASTM D7867	500-600

Grey
35.3 oz. Bottle (1 kg)
[6139-644]